

LL7410D1

Linear Low Density Polyethylene Resin

Special Characteristics : InnoPlus LL7410D1 resin is a linear low density polyethylene with butene comonomers, with low content of slip and antiblock. This grade offers the excellent machinability on conversion lines. Films extruded from InnoPlus LL7410D1 have high tensile strength, elongation, good toughness and outstanding puncture strength. It is available for tubular blown film processing.

Typical Applications : InnoPlus LL7410D1 is recommended for producing the general purpose films, liners, food packaging, heavy duty and agricultural films.

Typical Properties :

Properties	InnoPlus LL7410D1	Unit	Test Method
<i>Physical Properties</i>			
Melt Index (190 °C, 2.16 kg)	1.0	g/10 min	ASTM D1238
Density	0.920	g/cm ³	ASTM D792
Melting Point	121	°C	ASTM D3418
Vicat Softening Point	101	°C	ASTM D1525
<i>Film Properties*</i>			
Tensile Strength at Break (MD/TD)	34 / 26	MPa	ASTM D882
Elongation at Break (MD/TD)	600 / 800	%	ASTM D882
Tensile Modulus, 1% Secant (MD/TD)	190 / 230	MPa	ASTM D882
Dart Impact Strength	90	g	ASTM D1709
Tear Strength (MD/TD)	100 / 300	g	ASTM D1922
Haze	13	%	ASTM D1003
Gloss (45°)	50	-	ASTM D2457
* film properties obtained from 25 microns film which was blown film extruded at blow up ratio 2			

Processing Condition :

The recommended temperature setting is in the range of 160 - 180 °C for extruder and 170 - 190 °C for die zone.

Note : Properties reported here are typical values of the product, not to be considered as specifications.

PTT Global Chemical makes no representations as to the accuracy or completeness of the information contained herein.